

PHYSICAL PROPERTIES

Delaware Flagstone

Tested per ASTM C-119 · Conforming to ASTM C568

A. Delaware Flagstone

1. Region: Texas — San Saba Quarry
2. Limestone conforming to ASTM C568, with the following properties:

| TEST METHOD | PROPERTY | RESULT |
|-------------|-----------------------|-----------|
| ASTM C97 | Water Absorption | 6.02 % |
| ASTM C97 | Density | 141.4 pcf |
| ASTM C99 | Modulus of Rupture | 841 psi |
| ASTM C170 | Compressive Strength | 6,612 psi |
| ASTM C97 | Bulk Specific Gravity | 2.198 |

3. Face: Natural face
4. Cut: Irregular random shapes
5. Color: Tan, brown with red tones

Additional Data — Delaware Flagstone

| | |
|---------------------|---|
| DESCRIPTION | 4"-16" uniquely hand-made pieces of varying shapes |
| FULL STONE | 3"-5" thick · up to 16" widths |
| THIN VENEER | 1"-1.5" thick · up to 16" widths |
| HEIGHT TOLERANCE | Varies |
| FULL-STONE COVERAGE | ≈ 37 sq ft per ton · 74 sq ft per pallet |
| THIN-VENEER ORDER | Flats by the square foot · corners by the linear foot |
| THIN-VENEER CORNERS | 6"-10" leg · 3"-5" return |

Note: Testing is performed on small samples and may not reflect the specific stone you receive. Cooper Stone is a product of nature. Products of nature inherently lack uniformity and are subject to variation in aesthetics, color, shade, finish, tint, hardness, strength, resistance, density, and similar attributes. Cooper Stone LLC makes no warranties, either express or implied, of merchantability or fitness for a particular purpose.

Micah Flippen
Owner, Cooper Stone LLC